

SUPPLEMENTAL SPECIFICATIONS FOR STONE AND GRAVEL

GENERAL

The intent of this specification is to provide stone that is of uniform size and free of dust and fines for our surface treating (chip sealing) program. All stone shall be 100% crushed and washed.

MODIFIED #8 LIMESTONE

Estimated Quantity: 10,000 Tons

SIEVE SIZE: PERCENT PASSING:

No. 1/2"	100
No. 3/8"	85 - 95
No. 4.....	0 - 15
No. 8.....	0 - 2
No. 16.....	0 - 1

MODIFIED #9 LIMESTONE

Estimated Quantity: 4,000 Tons

SIEVE SIZE: PERCENT PASSING:

No. 3/8"	100
No. 4.....	100
No. 8.....	15 - 20
No. 16.....	0 - 5
No. 50.....	0 - 2

MATERIAL TESTING

The Madison County Engineer/representative reserves the right to request supplier provided gradation test for every 2,000 tons produced for material acceptance.